Material: Centrifugally Cast Gray Iron.

Application: Cylinder Liner & Sleeves

Specifications

American – Classification ASTM – A 48, Class 30 German – DIN 1691 GG 30

Chemical Composition

Element	С	Si	Mn	Р	S	Cr	Ni	Мо
(%)	3,0-3,6	2,0-2,7	0,5-0,9	0,2-0,65	<0,10	0-0,50	0-0,40	0-0,25

Other elements may be present as impurities.

Mechanical Properties

Hardness: 93 – 104 HRB, 210 – 260 HB Tensile Strength: min. 270 N/mm2

Microstructure

Graphite: Fine, Lamellar and uniformly distributed. Preferably type A, size between 5 and 7.



Matrix: Perlitic, with ferrite not exceeding 5%.

Note: Variations in composition ranges are admissible on condition that the structure and mechanical properties are not affected.